

ARM SLEEVES YELLOW FLUOR



IDEAL FOR

- Protection from UV rays while doing high intensity outdoor jobs in warm and hot weather conditions.
- With HeiQ Smart Temp cooling technology for a better comfort and reduction of heat exhaustion, fatigue and heat stroke risks.

CERTIFICATIONS

Solid Yellow Fluor:



UNE-EN 17353:2020



TYPE A EQUIPMENT
FOR DAYLIGHT

ENHANCED VISIBILITY EQUIPMENT FOR MEDIUM RISK SITUATIONS			
EN 17353:2020, Protective clothing. Enhanced visibility equipment for medium hazards situations			
Performance level	Type of clothing	Intended use	Design
	Type A	For daytime visibility only	Fluorescent material



SUN
PROTECTION

SKIN PROTECTION AGAINST NATURAL ULTRAVIOLET RADIATION					
Property	Standard	Performance value	Protection category	% UV radiation blocked	Effective UVR penetration (%)
UPF	AS/NZS 4399:2017	50 UPF	Excellent	98 %	≤ 2.0

KEY FEATURES



UPF
50



MOISTURE
MANAGEMENT



QUICK
DRY



4-WAY
ULTRA STRETCH



SILICONE
ADJUSTMENT



HEIQ
SMART TEMP



COOLING
EFFECT

DIMENSIONS



M

Upper arm fit circumference 26cm

Lower arm fit circumference 18cm

Outseam length 46cm

L

Upper arm fit circumference 30cm

Lower arm fit circumference 20cm

Outseam length 48cm

XL

Upper arm fit circumference 34cm

Lower arm fit circumference 22cm

Outseam length 50cm

FABRICS COMPOSITION

Fabric: 86% Polyester, 14% Elastane.

Elastic band: 83% Polyamide, 17% Elastane.

PACKAGING



WASHING MAINTENANCE SYMBOLS



Mass per unit area: EN 12127:1997		123 g/m ²	± 5 %
Air Permeability EN ISO 9237:1995		360 mm/s	± 10 %
Thermal Resistance (RCT): EN ISO 11092:2014		0,0041 m ² K/W	± 10 %
Water Vapour Resistance (RET): EN ISO 11092:2014		1,33 m ² Pa/W	± 10 %
Determination of breaking Strength and elongation: EN ISO 13934-1:2013			
		AVERAGE LOAD	AVERAGE ELONGATION
		LENGTHWISE	308 N ± 10 %
		CROSSWISE	174 N ± 10 %
		LENGTHWISE	277% ± 10 %
		CROSSWISE	376% ± 10 %
Bursting resistance: EN ISO 13938-1:2019		134,4 kPa	± 10 %
Determination of dimensional change in domestic washing and drying: EN ISO 5077:2008			
		LENGTHWISE < ±3%	CROSSWISE < ±3%
Washing procedure 4N (Ta=40 ±3°C) according to ISO 6330:2012			
Resistance to pilling: ISO 12945-2:2020		3 - 4	7000 CYCLES
Scale from 1 to 5 in which 1 is “Very severe pilling” and 5 is “No pilling”.			
Determination of the abrasion resistance of fabrics: EN ISO 12947-2:2016		>100.000 CYCLES	
Testing pressure: 9 kPa		Until the first yarn broken	
Fastness rates:			
Colour fastness to domestic and commercial laundering: EN ISO 105-C06:2010		3 *	
Colour fastness to perspiration (Alkaline & Acid): EN ISO 105-E04:2013		ALKALINE	4 *
		ACID	4 *
Colour fastness to rubbing (Dry & Wet): EN ISO 105-X12:2016		DRY	4 - 5 *
		WET	4 - 5 *
Colour fastness to sea water: EN ISO 105-E02:2013		4 *	
Colour fastness to artificial light: EN ISO 105-B02:2014 Method 2		5**	
* Fastness rates in a scale from 1 to 5 in which 1 is “Poor behaviour” and 5 is “Good behaviour”.			
** Fastness to artifical light rates in a scale from 1 to 8 in which 1 is “Very poor” and 8 is “Excelent”			
Enhanced Visibility		CHROMACITY COORDINATES	LUMINANCE FACTOR
CIE 15	YELLOW FLUOR	x = 0,3871	y = 0,5357
			β = 0,8145
Ultraviolet Protection: AS/NZS 4399:2017		50+ Excellent protection	